



kerakoll

DECLARATION OF PERFORMANCE No. 0480

1. Unique identification code of the product-type: **GeoSteel SRG**
(GeoSteel G600 and Geocalce F Antisismico/Geocalce FL Antisismico/Geolite/Geolite Magma)
2. Intended use/es: **The SRG kit is suitable for strengthening and seismic upgrade of clay, tuff, natural stone masonry and reinforced concrete elements and structures.**
3. Manufacturer: **Kerakoll S.p.A Via dell'Artigianato, 9 - 41049 Sassuolo (MO) Italia**
4. System/s of AVCP: **System 2+**
5. European Assessment Document: **EAD 340275-00-0104, January 2018**
European Technical Assessment : **ETA-19/0325 of 13/07/2022**
Technical Assessment Body: **ITC CNR**
Notified body/ies: **ITC n°0970**
6. Declared performance/s:
 - Characteristic value for tensile strength and tensile strain
 - Average value for modulus of elasticity

Essential characteristics	Performance
Reaction to fire	Class A1
GeoSteel G600 – Geocalce F Antisismico/Geocalce FL Antisismico/Geolite/Geolite Magma	See Annex A

The performance of the product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by: **Romano Sghedoni (legal representative)**

At Sassuolo, on 29/07/2022

kerakoll.com

KERAKOLL IBÉRICA S.A.U. – Carretera de Alcora, km. 10,450 – 12006 Castellón de la Plana – España
Tel. +34 964 251 500 – Fax +34 964 241 100 – e-mail: info@kerakoll.es

C.I.F. A-12331435. Inscrita en el Registro Mercantil de CASTELLÓN, TOMO 594, LIBRO 161, FOLIO 101, HOJA N.º CS 4393, INSC. I.ª SECC. G.



kerakoll

Annex A – GeoSteel G600-Geocalce F Antisismico /Geocalce FL Antisismico/Geolite /Geolite Magma

Essential characteristics			Performance	
			Average Value	Characteristic value
Direct Tensile Strength - Ambient				
Tensile strength (σ_u)		GL	2871 MPa	2697 MPa
Strain (ϵ_u)			1,65 %	1,38 %
Stress-strain curve (E)	Elastic modulus of stage A		2065 GPa	827 GPa
	Stiffness modulus in stage C		190 GPa	150 GPa
Tensile strength (σ_u)		GCF	2969 MPa	2798 MPa
Strain (ϵ_u)			1,81 %	1,42 %
Stress-strain curve (E)	Elastic modulus of stage A		1246 GPa	956 GPa
	Stiffness modulus in stage C		195 GPa	160 GPa
Direct Tensile Strength – maximum service temperature				
Tensile strength ($\sigma_{u, 80}$)		GL	2374 MPa	1939 MPa
Strain ($\epsilon_{u, 80}$)			1,24 %	1,09 %
Stress-strain curve ($E_{1, 80}; E_{3, 80}$)	Elastic modulus of stage A		1453 GPa	-(1)
	Stiffness modulus in stage C		191 GPa	150 GPa
Tensile strength ($\sigma_{u, 80}$)		GCF	2075 MPa	817 MPa
Strain ($\epsilon_{u, 80}$)			1,16 %	0,49 %
Stress-strain curve ($E_{1, 80}; E_{3, 80}$)	Elastic modulus of stage A		2225 GPa	-(1)
	Stiffness modulus in stage C		179 GPa	163 GPa
Interlaminar shear strength (τ)	G600 + GL		2.93 MPa	1.21 MPa
	G600 + GCF		1.45 MPa	0.65 MPa
Lap tensile strength (σ_{lap})	Tested Overlap length $l_{lap} = 300$ mm	GL	2675 MPa	2471 MPa
		GCF	2783 MPa	2434 MPa
Bond strength on substrate CONCRETE: pull-off test (f_h) G600+GL	ambient		2.83 MPa	-
	Water	1000 h	f_h 2.75 MPa $f_{h\ ret}$ 97 %	-
		3000 h	f_h 3.24 MPa $f_{h\ ret}$ 115 %	-
	saltwater	1000 h	f_h 2.89 MPa $f_{h\ ret}$ 102 %	-
		3000 h	f_h 3.43 MPa $f_{h\ ret}$ 121 %	-
	alkali	1000 h	f_h 2.95 MPa $f_{h\ ret}$ 104 %	-
		3000 h	f_h 3.68 MPa $f_{h\ ret}$ 130 %	-

kerakoll.com

KERAKOLL IBÉRICA S.A.U. – Carretera de Alcora, km. 10,450 – 12006 Castellón de la Plana – España

Tel. +34 964 251 500 – Fax +34 964 241 100 – e-mail: info@kerakoll.es

C.I.F. A-12331435. Inscrita en el Registro Mercantil de CASTELLÓN, TOMO 594, LIBRO 161, FOLIO 101, HOJA N.º CS 4393, INSC. I.ª SECC. G.



kerakoll

Essential characteristics			Performance	
			Average Value	Characteristic value
Bond strength on substrate CLAY: pull-off test (f_h) G600+GCF	ambient		1.47 MPa	-
	Water	1000 h	f_h 2.22 MPa $f_{h \text{ ret}}$ 152 %	-
		3000 h	f_h 2.32 MPa $f_{h \text{ ret}}$ 158 %	-
	saltwater	1000 h	f_h 1.85 MPa $f_{h \text{ ret}}$ 126 %	-
		3000 h	f_h 2.28 MPa $f_{h \text{ ret}}$ 156 %	-
	alkali	1000 h	f_h 2.74 MPa $f_{h \text{ ret}}$ 187 %	-
		3000 h	f_h 2.68 MPa $f_{h \text{ ret}}$ 183 %	-
	ambient		0.35 MPa	-
Bond strength on substrate TUFF: pull-off test (f_h) G600+GCF	Water	1000 h	f_h 0.50 MPa $f_{h \text{ ret}}$ 144 %	-
		3000 h	f_h 0.41 MPa $f_{h \text{ ret}}$ 117 %	-
	saltwater	1000 h	f_h 0.56 MPa $f_{h \text{ ret}}$ 162 %	-
		3000 h	f_h 0.46 MPa $f_{h \text{ ret}}$ 131 %	-
	alkali	1000 h	f_h 0.42 MPa $f_{h \text{ ret}}$ 120 %	-
		3000 h	f_h 0.45 MPa $f_{h \text{ ret}}$ 128 %	-
	ambient		0.35 MPa	-
	ambient		0.35 MPa	-

kerakoll.com

KERAKOLL IBÉRICA S.A.U. - Carretera de Alcora, km. 10,450 - 12006 Castellón de la Plana - España

Tel. +34 964 251 500 - Fax +34 964 241 100 - e-mail: info@kerakoll.es

C.I.F. A-12331435. Inscrita en el Registro Mercantil de CASTELLÓN, TOMO 594, LIBRO 161, FOLIO 101, HOJA N.º CS 4393, INSC. I.ª SECC. G.



kerakoll

Essential characteristics			Performance	
			Average Value	Characteristic value
Bond strength on substrate CONCRETE: single-lap shear test G600+GL	ambient		P_{max} 10143 N P_{deb} 8683 N $\sigma_{lim,conv}$ 2357 MPa	P_{max} 7865 N P_{deb} 4799 N $\sigma_{lim,conv}$ 1827 MPa
	Water	1000 h	P_{max} 10574 N P_{deb} 10040 N $P_{max ret}$ 104 % $P_{deb ret}$ 116 %	-
		3000 h	P_{max} 10682 N P_{deb} 9727 N $P_{max ret}$ 105 % $P_{deb ret}$ 112 %	-
	saltwater	1000 h	P_{max} 11008 N P_{deb} 10048 N $P_{max ret}$ 109 % $P_{deb ret}$ 116 %	-
		3000 h	P_{max} 8597 N P_{deb} - $P_{max ret}$ 85 % $P_{deb ret}$ -	-
	alkali	1000 h	P_{max} 11946 N P_{deb} 10939 N $P_{max ret}$ 118 % $P_{deb ret}$ 126 %	-
		3000 h	P_{max} 11594 N P_{deb} 10872 N $P_{max ret}$ 114 % $P_{deb ret}$ 125 %	-

kerakoll.com

KERAKOLL IBÉRICA S.A.U. - Carretera de Alcora, km. 10,450 - 12006 Castellón de la Plana - España

Tel. +34 964 251 500 - Fax +34 964 241 100 - e-mail: info@kerakoll.es

C.I.F. A-12331435. Inscrita en el Registro Mercantil de CASTELLÓN, TOMO 594, LIBRO 161, FOLIO 101, HOJA N.º CS 4393, INSC. I.ª SECC. G.



kerakoll

Essential characteristics			Performance	
			Average Value	Characteristic value
Bond strength on substrate CLAY: single-lap shear test G600+GCF	ambient		P _{max} 10158 N P _{deb} 8504 N σ _{lim,conv} 2360 MPa	P _{max} 7606 N P _{deb} 4152 N σ _{lim,conv} 1767 MPa
	Water	1000 h	P _{max} 9632 N P _{deb} 8728 N P _{max ret} 95 % P _{deb ret} 103 %	-
		3000 h	P _{max} 7803 N P _{deb} 6416 N P _{max ret} 77 % P _{deb ret} 75 %	-
	saltwater	1000 h	P _{max} 8946 N P _{deb} 8315 N P _{max ret} 88 % P _{deb ret} 98 %	-
		3000 h	P _{max} 8577 N P _{deb} 8238 N P _{max ret} 84 % P _{deb ret} 97 %	-
	alkali	1000 h	P _{max} 8727 N P _{deb} 7217 N P _{max ret} 86 % P _{deb ret} 85 %	-
		3000 h	P _{max} 8917 N P _{deb} 7693 N P _{max ret} 88 % P _{deb ret} 90 %	-
	ambient		P _{max} 7488 N P _{deb} 6322 N σ _{lim,conv} 1740 MPa	P _{max} 6855 N P _{deb} 4297 N σ _{lim,conv} 1593 MPa
	Bond strength on substrate TUFF: single-lap shear test G600+GCF	Water	1000 h	P _{max} 7378 N P _{deb} 6859 N P _{max ret} 99 % P _{deb ret} 109 %
3000 h			P _{max} 8183 N P _{deb} 7200 N P _{max ret} 109 % P _{deb ret} 114 %	-
saltwater		1000 h	P _{max} 7493 N P _{deb} 7305 N P _{max ret} 100 % P _{deb ret} 116 %	-
		3000 h	P _{max} 6669 N P _{deb} 6313 N P _{max ret} 89 % P _{deb ret} 100 %	-

kerakoll.com

KERAKOLL IBÉRICA S.A.U. - Carretera de Alcora, km. 10,450 - 12006 Castellón de la Plana - España

Tel. +34 964 251 500 - Fax +34 964 241 100 - e-mail: info@kerakoll.es

C.I.F. A-12331435. Inscrita en el Registro Mercantil de CASTELLÓN, TOMO 594, LIBRO 161, FOLIO 101, HOJA N.º CS 4393, INSC. I.ª SECC. G.



kerakoll

	alkali	1000 h	P_{max} 7277 N P_{deb} 6375 N $P_{max\ ret}$ 97 % $P_{deb\ ret}$ 101 %	-
		3000 h	P_{max} 7221 N P_{deb} 6601 N $P_{max\ ret}$ 96 % $P_{deb\ ret}$ 105 %	-
Bond strength on substrate NATURAL STONE: single-lap shear test G600+GCF	ambient		P_{max} 11801 N P_{deb} - (2) $\sigma_{lim,conv}$ 2742 MPa	P_{max} 10636 N P_{deb} - (2) $\sigma_{lim,conv}$ 2471 MPa
Pull out from substrate CONCRETE: (failure mode FR) G600+GLM	ambient		$\sigma_{pull-out}$ 2525 MPa $\delta_{pull-out}$ 7,2 mm	-
	Water	1000 h	$\sigma_{pull-out}$ 2549 MPa $\delta_{pull-out}$ 5.30 mm $\sigma_{pull-out\ ret}$ 101%	-
		3000 h	$\sigma_{pull-out}$ 2634 MPa $\delta_{pull-out}$ 7.81 mm $\sigma_{pull-out\ ret}$ 104 %	-
	saltwater	1000 h	$\sigma_{pull-out}$ 2491 MPa $\delta_{pull-out}$ 7.40 mm $\sigma_{pull-out\ ret}$ 97%	-
		3000 h	$\sigma_{pull-out}$ 2340 MPa $\delta_{pull-out}$ 5.20 mm $\sigma_{pull-out\ ret}$ 93%	-
	alkali	1000 h	$\sigma_{pull-out}$ 2712 MPa $\delta_{pull-out}$ 6.04 mm $\sigma_{pull-out\ ret}$ 107 %	-
		3000 h	$\sigma_{pull-out}$ 2522 MPa $\delta_{pull-out}$ 5.50 mm $\sigma_{pull-out\ ret}$ 100 %	-

kerakoll.com

KERAKOLL IBÉRICA S.A.U. - Carretera de Alcora, km. 10,450 - 12006 Castellón de la Plana - España

Tel. +34 964 251 500 - Fax +34 964 241 100 - e-mail: info@kerakoll.es

C.I.F. A-12331435. Inscrita en el Registro Mercantil de CASTELLÓN, TOMO 594, LIBRO 161, FOLIO 101, HOJA N.º CS 4393, INSC. I.ª SECC. G.



kerakoll

Pull out from substrate CLAY: (failure mode FR) G600+GCFL	ambient		$\sigma_{\text{pull-out}}$ 2709 MPa $\delta_{\text{pull-out}}$ 7,7 mm	-
	Water	1000 h	$\sigma_{\text{pull-out}}$ 2555 MPa $\delta_{\text{pull-out}}$ 6.94 mm $\sigma_{\text{pull-out ret}}$ 94 %	-
		3000 h	$\sigma_{\text{pull-out}}$ 2510 MPa $\delta_{\text{pull-out}}$ 6.28 mm $\sigma_{\text{pull-out ret}}$ 93 %	-
	saltwater	1000 h	$\sigma_{\text{pull-out}}$ 2575 MPa $\delta_{\text{pull-out}}$ 7.70 mm $\sigma_{\text{pull-out ret}}$ 95 %	-
		3000 h	$\sigma_{\text{pull-out}}$ 2542 MPa $\delta_{\text{pull-out}}$ 7.12 mm $\sigma_{\text{pull-out ret}}$ 94 %	-
	alkali	1000 h	$\sigma_{\text{pull-out}}$ 2593 MPa $\delta_{\text{pull-out}}$ 7.19 mm $\sigma_{\text{pull-out ret}}$ 96 %	-
		3000 h	$\sigma_{\text{pull-out}}$ 2642 MPa $\delta_{\text{pull-out}}$ 7.30 mm $\sigma_{\text{pull-out ret}}$ 98 %	-
	ambient		$\sigma_{\text{pull-out}}$ 2503 MPa $\delta_{\text{pull-out}}$ 8,3 mm	-
Pull out from substrate TUFF: (failure mode FR) G600+ GCFL	Water	1000 h	$\sigma_{\text{pull-out}}$ 2803 MPa $\delta_{\text{pull-out}}$ 8.32 mm $\sigma_{\text{pull-out ret}}$ 112 %	-
		3000 h	$\sigma_{\text{pull-out}}$ 2730 MPa $\delta_{\text{pull-out}}$ 8.06 mm $\sigma_{\text{pull-out ret}}$ 109 %	-
	saltwater	1000 h	$\sigma_{\text{pull-out}}$ 2480 MPa $\delta_{\text{pull-out}}$ 8.34 mm $\sigma_{\text{pull-out ret}}$ 99 %	-
		3000 h	$\sigma_{\text{pull-out}}$ 2665 MPa $\delta_{\text{pull-out}}$ 7.70 mm $\sigma_{\text{pull-out ret}}$ 106 %	-
	alkali	1000 h	$\sigma_{\text{pull-out}}$ 2557 MPa $\delta_{\text{pull-out}}$ 7.62 mm $\sigma_{\text{pull-out ret}}$ 102 %	-
		3000 h	$\sigma_{\text{pull-out}}$ 2616 MPa $\delta_{\text{pull-out}}$ 7.48 mm $\sigma_{\text{pull-out ret}}$ 105 %	-
	ambient		$\sigma_{\text{pull-out}}$ 2503 MPa $\delta_{\text{pull-out}}$ 8,3 mm	-
	ambient		$\sigma_{\text{pull-out}}$ 2503 MPa $\delta_{\text{pull-out}}$ 8,3 mm	-

GL = GeoLite; GCF = Geocalce F Antisismico

kerakoll.com

KERAKOLL IBÉRICA S.A.U. - Carretera de Alcora, km. 10,450 - 12006 Castellón de la Plan:

Tel. +34 964 251 500 - Fax +34 964 241 100 - e-mail: info@kerakoll.es

C.I.F. A-12331435. Inscrita en el Registro Mercantil de CASTELLÓN, TOMO 594, LIBRO 161, FOLIO 101, HOJA N.º CS 4393, INSC. I.ª SECC. G.



kerakoll

Essential characteristics			Performance		
				Average value	Characteristic value
Freezing and Thawing	Direct tension	GL	Tensile strength $\sigma_{u,FT}$ Strain $\varepsilon_{u,FT}$ Stiffness moduli E_{1FT} Stiffness moduli E_{3FT} Inter shear strength (τ_{FT})	2561 MPa 1,55 % NPA 183 GPa 3.61 Mpa	2423 MPa 1,36 % NPA 163 GPa 2.73 Mpa
		GCF	Tensile strength $\sigma_{u,FT}$ Strain $\varepsilon_{u,FT}$ Stiffness moduli E_{1FT} Stiffness moduli E_{3FT} Inter shear strength (τ_{FT})	2832 MPa 1,80 % NPA 199 GPa 1.54 MPa	2709 MPa 1,57 % NPA 173 GPa 1.03 MPa
	Retained properties	GL	Tensile strength $\sigma_{u,FT,ret}$ Stiffness moduli $E_{1FT,ret}$ Stiffness moduli $E_{3FT,ret}$ Inter shear strength ($\tau_{FT,ret}$)	89% NPA 97% 123 %	-
		GCF	Tensile strength $\sigma_{u,FT,ret}$ Stiffness moduli $E_{1FT,ret}$ Stiffness moduli $E_{3FT,ret}$ Inter shear strength ($\tau_{FT,ret}$)	95% NPA 103% 106%	-
Water resistance	Direct tension (1000 h)	GL	Tensile strength $\sigma_{u,w}$ Strain $\varepsilon_{u,w}$ Stiffness moduli E_{1w} Stiffness moduli E_{3w} Inter. shear strength (τ_w) Lap tensile ($\sigma_{lap,w}$)	2532 MPa 1,61 % NPA 217 GPa 3.81 MPa NPA	2377 MPa 1,31 % NPA 178 GPa 2.95 MPa NPA
		GCF	Tensile strength $\sigma_{u,w}$ Strain $\varepsilon_{u,w}$ Stiffness moduli E_{1w} Stiffness moduli E_{3w} Inter. shear strength (τ_w) Lap tensile ($\sigma_{lap,w}$)	2528 MPa 1,92 % NPA 246 GPa 1.04 MPa NPA	2489 MPa 1,61 % NPA 166 GPa 0.70 MPa NPA
	Direct tension (3000 h)	GL	Tensile strength $\sigma_{u,w}$ Strain $\varepsilon_{u,w}$ Stiffness moduli E_{1w} Stiffness moduli E_{3w} Inter. shear strength (τ_w) Lap tensile ($\sigma_{lap,w}$)	2806 MPa 1,57 % NPA 281 GPa 4.92 MPa NPA	2705 MPa 1,39 % NPA 239 GPa 3.85 MPa NPA
		GCF	Tensile strength $\sigma_{u,w}$ Strain $\varepsilon_{u,w}$ Stiffness moduli E_{1w} Stiffness moduli E_{3w} Inter. shear strength (τ_w) Lap tensile ($\sigma_{lap,w}$)	2585 MPa 1,88 % NPA 199 GPa 1.97 MPa NPA	2514 MPa 1,55 % NPA 155 GPa 1.48 MPa NPA
	Retained properties (1000 h)	GL	Tensile strength $\sigma_{u,w,ret}$ Stiffness moduli $E_{1w,ret}$ Stiffness moduli $E_{3w,ret}$ Inter. shear strength ($\tau_{w,ret}$) Lap tensile ($\sigma_{lap,w,ret}$)	88 % NPA 115 % 130 % NPA	-
		GCF	Tensile strength $\sigma_{u,w,ret}$ Stiffness moduli $E_{1w,ret}$ Stiffness moduli $E_{3w,ret}$ Inter. shear strength ($\tau_{w,ret}$) Lap tensile ($\sigma_{lap,w,ret}$)	85 % NPA 127 % 72 % NPA	-
	Retained properties (3000 h)	GL	Tensile strength $\sigma_{u,w,ret}$ Stiffness moduli $E_{1w,ret}$ Stiffness moduli $E_{3w,ret}$ Inter. shear strength ($\tau_{w,ret}$) Lap tensile ($\sigma_{lap,w,ret}$)	98 % NPA 149 % 168 % NPA	-

kerakoll.com

KERAKOLL IBÉRICA S.A.U. - Carretera de Alcora, km. 10,450 - 12006 Castellón de la Plana - España

Tel. +34 964 251 500 - Fax +34 964 241 100 - e-mail: info@kerakoll.es

C.I.F. A-12331435. Inscrita en el Registro Mercantil de CASTELLÓN, TOMO 594, LIBRO 161, FOLIO 101, HOJA N.º CS 4393, INSC. I.ª SECC. G.



kerakoll

		GCF	Tensile strength $\sigma_{u, w, ret}$ Stiffness moduli $E_{1 w, ret}$ Stiffness moduli $E_{3 w, ret}$ Inter. shear strength ($\tau_{w ret}$) Lap tensile ($\sigma_{lap w ret}$)	87 % NPA 103 % 136 % NPA	-
--	--	-----	---	--------------------------------------	---

GL = GeoLite; GCF = Geocalce F Antisismico

Refresca

Essential characteristics			Performance		
				Average value	Characteristic value
Saltwater resistance	Direct tension (1000 h)	GL	Tensile strength $\sigma_{u, sw}$ Strain $\epsilon_{u, sw}$ Stiffness moduli $E_{1 sw}$ Stiffness moduli $E_{3 sw}$ Inter. shear strength (τ_{sw}) Lap tensile ($\sigma_{lap sw}$)	2819 MPa 1,59 % NPA 189 GPa 3.94 MPa NPA	2622 MPa 1,31 % NPA 162 GPa 3.10 MPa NPA
			Tensile strength $\sigma_{u, sw}$ Strain $\epsilon_{u, sw}$ Stiffness moduli $E_{1 sw}$ Stiffness moduli $E_{3 sw}$ Inter. shear strength (τ_{sw}) Lap tensile ($\sigma_{lap sw}$)	2712 MPa 1,92 % NPA 229 GPa 0.62 MPa NPA	2639 MPa 1,63 % NPA 197 GPa 0.44 MPa NPA
		GL	Tensile strength $\sigma_{u, sw}$ Strain $\epsilon_{u, sw}$ Stiffness moduli $E_{1 sw}$ Stiffness moduli $E_{3 sw}$ Inter. shear strength (τ_{sw}) Lap tensile ($\sigma_{lap sw}$)	2933 MPa 1,57 % NPA 182 GPa 3.73 MPa NPA	2765 MPa 1,33 % NPA 161 GPa 3.19 MPa NPA
			Tensile strength $\sigma_{u, sw}$ Strain $\epsilon_{u, sw}$ Stiffness moduli $E_{1 sw}$ Stiffness moduli $E_{3 sw}$ Inter. shear strength (τ_{sw}) Lap tensile ($\sigma_{lap sw}$)	2542 MPa 1,77 % NPA 184 GPa 1.28 MPa NPA	2470 MPa 1,55 % NPA 160 GPa 0.77 MPa NPA
	Retained properties (1000 h)	GL	Tensile strength $\sigma_{u, sw, ret}$ Stiffness moduli $E_{1 sw, ret}$ Stiffness moduli $E_{3 sw, ret}$ Inter. shear strength ($\tau_{sw ret}$) Lap tensile ($\sigma_{lap sw ret}$)	98 % NPA 100 % 135 % NPA	-
			Tensile strength $\sigma_{u, sw, ret}$ Stiffness moduli $E_{1 sw, ret}$ Stiffness moduli $E_{3 sw, ret}$ Inter. shear strength ($\tau_{sw ret}$) Lap tensile ($\sigma_{lap sw ret}$)	91 % NPA 118 % 43 % NPA	-
		GL	Tensile strength $\sigma_{u, sw, ret}$ Stiffness moduli $E_{1 sw, ret}$ Stiffness moduli $E_{3 sw, ret}$ Inter. shear strength ($\tau_{sw ret}$) Lap tensile ($\sigma_{lap sw ret}$)	102 % NPA 96 % 127 % NPA	-
			Tensile strength $\sigma_{u, sw, ret}$ Stiffness moduli $E_{1 sw, ret}$ Stiffness moduli $E_{3 sw, ret}$ Inter. shear strength ($\tau_{sw ret}$) Lap tensile ($\sigma_{lap sw ret}$)	86 % NPA 95 % 88 % NPA	-

kerakoll.com

KERAKOLL IBÉRICA S.A.U. - Carretera de Alcora, km. 10,450 - 12006 Castellón de la Plana - España

Tel. +34 964 251 500 - Fax +34 964 241 100 - e-mail: info@kerakoll.es

C.I.F. A-12331435. Inscrita en el Registro Mercantil de CASTELLÓN, TOMO 594, LIBRO 161, FOLIO 101, HOJA N.º CS 4393, INSC. I.ª SECC. G.



kerakoll

Alkali resistance	Direct tension (1000 h)	GL	Tensile strength $\sigma_{u, alk}$ Strain $\epsilon_{u, alk}$ Stiffness moduli $E_{1 alk}$ Stiffness moduli $E_{3 alk}$ Inter. shear strength (τ_{alk}) Lap tensile ($\sigma_{lap alk}$) NPA	2917 MPa 1,66 % NPA 187 GPa 4.18 MPa NPA	2755 MPa 1,47 % NPA 156 GPa 3.45 MPa NPA
		GCF	Tensile strength $\sigma_{u, alk}$ Strain $\epsilon_{u, alk}$ Stiffness moduli $E_{1 alk}$ Stiffness moduli $E_{3 alk}$ Inter. shear strength (τ_{alk}) Lap tensile ($\sigma_{lap alk}$)	2713 MPa 2,15 % NPA 218 GPa 0.62 MPa NPA	2604 MPa 1,76 % NPA 170 GPa 0.53 MPa NPA
	Direct tension (3000 h)	GL	Tensile strength $\sigma_{u, alk}$ Strain $\epsilon_{u, alk}$ Stiffness moduli $E_{1 alk}$ Stiffness moduli $E_{3 alk}$ Inter. shear strength (τ_{alk}) Lap tensile ($\sigma_{lap alk}$)	3007 MPa 1,67 % NPA 186 GPa 3.61 MPa NPA	2855 MPa 1,47 % NPA 160 GPa 2.55 MPa NPA
		GCF	Tensile strength $\sigma_{u, alk}$ Strain $\epsilon_{u, alk}$ Stiffness moduli $E_{1 alk}$ Stiffness moduli $E_{3 alk}$ Inter. shear strength (τ_{alk}) Lap tensile ($\sigma_{lap alk}$)	2627 MPa 1,88 % NPA 207 GPa 1.59 MPa NPA	2519 MPa 1,59 % NPA 169 GPa 1.23 MPa NPA
	Retained properties (1000 h)	GL	Tensile strength $\sigma_{u, alk, ret}$ Stiffness moduli $E_{1 alk, ret}$ Stiffness moduli $E_{3 alk, ret}$ Inter. shear strength ($\tau_{alk ret}$) Lap tensile ($\sigma_{lap alk ret}$)	102 % NPA 99 % 143 % NPA	-
		GCF	Tensile strength $\sigma_{u, alk, ret}$ Stiffness moduli $E_{1 alk, ret}$ Stiffness moduli $E_{3 alk, ret}$ Inter. shear strength ($\tau_{alk ret}$) Lap tensile ($\sigma_{lap alk ret}$)	91 % NPA 112 % 43 % NPA	-

GL = GeoLite; GCF = Geocalce F Antisismico

kerakoll.com

KERAKOLL IBÉRICA S.A.U. - Carretera de Alcora, km. 10,450 - 12006 Castellón de la Plana - España

Tel. +34 964 251 500 - Fax +34 964 241 100 - e-mail: info@kerakoll.es

C.I.F. A-12331435. Inscrita en el Registro Mercantil de CASTELLÓN, TOMO 594, LIBRO 161, FOLIO 101, HOJA N.º CS 4393, INSC. I.ª SECC. G.



kerakoll

Essential characteristics			Performance		
				Average value	Characteristic value
Alkali resistance	Retained properties (3000 h)	GL	Tensile strength $\sigma_{u, alk, ret}$ Stiffness moduli $E_{1 alk, ret}$; Stiffness moduli $E_{3 alk, ret}$ Inter. shear strength ($\tau_{alk ret}$) Lap tensile ($\sigma_{lap alk ret}$)	105 % NPA 98 % 123 % NPA	-
		GCF	Tensile strength $\sigma_{u, alk, ret}$ Stiffness moduli $E_{1 alk, ret}$; Stiffness moduli $E_{3 alk, ret}$ Inter. shear strength ($\tau_{alk ret}$) Lap tensile ($\sigma_{lap alk ret}$)	89 % NPA 107 % 109 % NPA	-
Alkali soil resistance	GL	Direct tension (1000 h)	Tensile strength $\sigma_{u, soil}$ Strain $\varepsilon_{u, soil}$ Stiffness moduli $E_{1 soil}$; Stiffness moduli $E_{3 soil}$	2744 MPa 1.61 % 1301 GPa 175 GPa _i	2414 MPa 1.07 % 716 GPa 150 GPa _i
		Retained properties (1000 h)	Tensile strength $\sigma_{u, soil, ret}$ Stiffness moduli $E_{1 soil, ret}$; Stiffness moduli $E_{3 soil, ret}$	96 % 63 % 92 %	-
	GCF	Direct tension (1000 h)	Tensile strength $\sigma_{u, soil}$ Strain $\varepsilon_{u, soil}$ Stiffness moduli $E_{1 soil}$; Stiffness moduli $E_{3 soil}$	2687 MPa 1.49 % 1576 GPa 186 GPa	2169 MPa 0.89 % 790 GPa 162 GPa
		Retained properties (1000 h)	Tensile strength $\sigma_{u, soil, ret}$ Stiffness moduli $E_{1 soil, ret}$; Stiffness moduli $E_{3 soil, ret}$	91 % 127 % 96 %	-
Dry heat resistance	GL	Direct tension (1000 h)	Tensile strength $\sigma_{u, heat}$ Strain $\varepsilon_{u, heat}$ Stiffness moduli $E_{1 heat}$ Stiffness moduli $E_{3 heat}$	2817 MPa 1.73 % 1379 GPa _i 194 GPa _i	2560 MPa 1.49 % 677 GPa _i 172 GPa _i
		Retained properties (1000 h)	Tensile strength $\sigma_{u, heat, ret}$ Stiffness moduli $E_{1 heat, ret}$; Stiffness moduli $E_{3 heat, ret}$	98 % 67 % 102 %	-
		Direct tension (3000 h)	Tensile strength $\sigma_{u, heat}$ Strain $\varepsilon_{u, heat}$ Stiffness moduli $E_{1 heat}$ Stiffness moduli $E_{3 heat}$	2778 MPa 1.37 % 2069 GPa _i 215 GPa	2247 MPa 0.63 % 22 GPa _i 166 GPa
		Retained properties (3000 h)	Tensile strength $\sigma_{u, heat, ret}$ Stiffness moduli $E_{1 heat, ret}$; Stiffness moduli $E_{3 heat, ret}$	97 % 100 % 114 %	-
	GCF	Direct tension (1000 h)	Tensile strength $\sigma_{u, heat}$ Strain $\varepsilon_{u, heat}$ Stiffness moduli $E_{1 heat}$ Stiffness moduli $E_{3 heat}$	3102 MPa 1.53 % 1233 GPa 221 GPa	3056 MPa 1.43 % 551 GPa 196 GPa
		Retained properties (1000 h)	Tensile strength $\sigma_{u, heat, ret}$ Stiffness moduli $E_{1 heat, ret}$; Stiffness moduli $E_{3 heat, ret}$	104 % 99 % 114 %	-

kerakoll.com

KERAKOLL IBÉRICA S.A.U. - Carretera de Alcora, km. 10,450 - 12006 Castellón de la Plana - España

Tel. +34 964 251 500 - Fax +34 964 241 100 - e-mail: info@kerakoll.es

C.I.F. A-12331435. Inscrita en el Registro Mercantil de CASTELLÓN, TOMO 594, LIBRO 161, FOLIO 101, HOJA N.º CS 4393, INSC. I.ª SECC. G.



kerakoll

		Direct tension (3000 h)		Tensile strength $\sigma_{u, \text{heat}}$ Strain $\varepsilon_{u, \text{heat}}$ Stiffness moduli $E_{1 \text{ heat}}$ Stiffness moduli $E_{3 \text{ heat}}$	3133 MPa 1.75 % 1232 GPa; 197 GPa	3017 MPa 1.49 % 175 GPa; 175 GPa	
		Retained properties (3000 h)		Tensile strength $\sigma_{u, \text{heat,ret}}$ Stiffness moduli $E_{1 \text{ heat,ret}}$ Stiffness moduli $E_{3 \text{ heat,ret}}$	106 % 99 % 102 %	-	
Fuel resistance	GL	Direct tension		Tensile strength $\sigma_{u, \text{fuel}}$ Strain $\varepsilon_{u, \text{fuel}}$ Stiffness moduli $E_{1 \text{ fuel}}$ Stiffness moduli $E_{3 \text{ fuel}}$	1209 MPa 1.30 % NPA 81.9 GPa	1040 MPa 1.04 % NPA 70.9 GPa	
		Retained properties		Tensile strength $\sigma_{u, \text{fuel,ret}}$ Stiffness moduli $E_{1 \text{ fuel,ret}}$ Stiffness moduli $E_{3 \text{ fuel,ret}}$	42 % NPA 43 %	-	
	GCF	Direct tension		Tensile strength $\sigma_{u, \text{fuel}}$ Strain $\varepsilon_{u, \text{fuel}}$ Stiffness moduli $E_{1 \text{ fuel}}$ Stiffness moduli $E_{3 \text{ fuel}}$	809 MPa 1.44 % NPA 70.9 GPa	617 MPa 0.61 % NPA 52.2 GPa	
		Retained properties		Tensile strength $\sigma_{u, \text{fuel,ret}}$ Stiffness moduli $E_{1 \text{ fuel,ret}}$ Stiffness moduli $E_{3 \text{ fuel,ret}}$	27 % NPA 36 %	-	
	Creep behaviour related to the adhesion on substrate	Substrate: concrete		Displacement vs time (tabular)		0.023 mm	-
				Maximum load $P_{\text{max, creep}}$		8898 N	-(1)
Bond capacity $P_{\text{max, creep}}$				8268 N	8268 N		
Substrate: clay		Displacement vs time (tabular)		0.010 mm	-		
		Maximum load $P_{\text{max, creep}}$		8154 N	5402 N		
		Bond capacity $P_{\text{max, creep}}$		7605 N	7605 N		
Substrate: tuff		Displacement vs time (tabular)		0.007 mm	-		
		Maximum load $P_{\text{max, creep}}$		3484 N	2795 N		
		Bond capacity $P_{\text{max, creep}}$		3248 N	3248 N		
Tensile strength after long term actions (creep) - GL	100 h	Direct tension		Tensile strength $\sigma_{u, \text{creep}}$ Strain $\varepsilon_{u, \text{creep}}$ Stiffness moduli $E_{3 \text{ creep}}$	2994 MPa 1.72 % 221 GPa;	-	
		Retained properties		Tensile strength $\sigma_{u, \text{creep,ret}}$ Stiffness moduli $E_{3 \text{ creep,ret}}$	104 % 117 %	-	
	500 h	Direct tension		Tensile strength $\sigma_{u, \text{creep}}$ Strain $\varepsilon_{u, \text{creep}}$ Stiffness moduli $E_{3 \text{ creep}}$	3027 MPa 1.94 % 209 GPa	-	
		Retained properties		Tensile strength $\sigma_{u, \text{creep,ret}}$ Stiffness moduli $E_{3 \text{ creep,ret}}$	105 % 110 %	-	
	1000 h	Direct tension		Tensile strength $\sigma_{u, \text{creep}}$ Strain $\varepsilon_{u, \text{creep}}$ Stiffness moduli $E_{3 \text{ creep}}$	3001 MPa 1.72 % 215 GPa	-	
		Retained properties		Tensile strength $\sigma_{u, \text{creep,ret}}$ Stiffness moduli $E_{3 \text{ creep,ret}}$	105 % 113 %	-	
	4000 h	Direct tension		Tensile strength $\sigma_{u, \text{creep}}$ Strain $\varepsilon_{u, \text{creep}}$ Stiffness moduli $E_{3 \text{ creep}}$	3007 MPa 1.63 % 223 GPa	-	
		Retained properties		Tensile strength $\sigma_{u, \text{creep,ret}}$ Stiffness moduli $E_{3 \text{ creep,ret}}$	105 % 118 %	-	

kerakoll.com

KERAKOLL IBÉRICA S.A.U. - Carretera de Alcora, km. 10,450 - 12006 Castellón de la Plana - España

Tel. +34 964 251 500 - Fax +34 964 241 100 - e-mail: info@kerakoll.es

C.I.F. A-12331435. Inscrita en el Registro Mercantil de CASTELLÓN, TOMO 594, LIBRO 161, FOLIO 101, HOJA N.º CS 4393, INSC. I.ª SECC. G.



kerakoll

Essential characteristics			Performance		
				Average value	Characteristic value
Tensile strength after long term actions (creep) - GCF	100 h	Direct tension	Tensile strength $\sigma_{u, creep} \geq$ Strain $\varepsilon_{u, creep}$ Stiffness moduli $E_{3 creep}$	2702 MPa 1.48 % 218 GPa	-
		Retained properties	Tensile strength $\sigma_{u, creep, ret}$ Stiffness moduli $E_{3 creep, ret}$	91 % 112 %	-
	500 h	Direct tension	Tensile strength $\sigma_{u, creep}$ Strain $\varepsilon_{u, creep}$ Stiffness moduli $E_{3 creep}$	2725 MPa 1.58 % 210 GPa	-
		Retained properties	Tensile strength $\sigma_{u, creep, ret}$ Stiffness moduli $E_{3 creep, ret}$	92 % 108 %	-
	1000 h	Direct tension	Tensile strength $\sigma_{u, creep}$ Strain $\varepsilon_{u, creep}$ Stiffness moduli $E_{3 creep}$	2858 MPa 1.52 % 217 GPa	-
		Retained properties	Tensile strength $\sigma_{u, creep, ret}$ Stiffness moduli $E_{3 creep, ret}$	96 % 111 %	-
	4000 h	Direct tension	Tensile strength $\sigma_{u, creep}$ Strain $\varepsilon_{u, creep}$ Stiffness moduli $E_{3 creep}$	3014 MPa 1.68 % 224 GPa	-
		Retained properties	Tensile strength $\sigma_{u, creep, ret}$ Stiffness moduli $E_{3 creep, ret}$	102 % 115 %	-
Tensile strength after low number of cycles (seismic behaviour)	GL		Tensile strength $\sigma_{u, seismic}$ Strain $\varepsilon_{u, seismic}$ Stiffness moduli $E_{1 seismic, ret}$ Stiffness moduli $E_{3 seismic, ret}$	3004 MPa 1.78 % 2080 GPa 200 GPa	2910 MPa 1.65 % 452 GPa 170 GPa
	GCF		Tensile strength $\sigma_{u, seismic}$ Strain $\varepsilon_{u, seismic}$ Stiffness moduli $E_{1 seismic, ret}$ Stiffness moduli $E_{3 seismic, ret}$	3063 MPa 2.00 % 1218 GPa 193 GPa	3024 MPa 1.92 % 549 GPa 188 GPa
Tensile strength after high number of cycles (fatigue actions)				NPA	
Mechanical properties of fabric	5 cords		Ultimate stress $\sigma_{u, f}$ Ultimate strain $\varepsilon_{u, f}$ Mean elastic modulus E_f	3124 MPa 2,06 % 190 GPa	2942 MPa 1,54 % 142 GPa
	8 cords		Ultimate stress $\sigma_{u, f}$ Ultimate strain $\varepsilon_{u, f}$ Mean elastic modulus E_f	3087 MPa 2,07 % 195 GPa	2889 MPa 1,67 % 161 GPa
	8 cords	concrete + GL clay + GCF tuff + GCF natural stone+ GCF	$\varepsilon_{lim, conv}$	1,21 %	0,94 %
			$\varepsilon_{lim, conv}$	1,21 %	0.91 %
Tensile strength on bent fabric	Straight fabric		$\sigma_{u, f, straight}$ $\sigma_{u, f, straight+sw1000}$ $\sigma_{u, f, straight+sw3000}$	3118 MPa 2965 MPa 2535 MPa	2959 MPa 2794 MPa 2416 MPa
	Bent fabric		$\sigma_{u, f, bent}$ $\sigma_{u, f, bent+sw1000}$ $\sigma_{u, f, bent+sw3000}$	2652 MPa 2330 MPa 2165 MPa	2416 MPa 2195 MPa 2006 MPa

GL = GeoLite; GCF = Geocalce F Antisismico

- (1) value not determinable due to the high dispersion of results
- (2) Rupture of fibres was observed outside the bonded length

kerakoll.com

KERAKOLL IBÉRICA S.A.U. - Carretera de Alcora, km. 10,450 - 12006 Castellón de la Plana - España

Tel. +34 964 251 500 - Fax +34 964 241 100 - e-mail: info@kerakoll.es

C.I.F. A-12331435. Inscrita en el Registro Mercantil de CASTELLÓN, TOMO 594, LIBRO 161, FOLIO 101, HOJA N.º CS 4393, INSC. I.ª SECC. G.