

Pragma Super

Mineral adhesive for high adhesion and high-performance laying of tiles. Suitable for laying tiles on mineral or cement-based substrates.



1. For internal floors and walls
2. Polymer-modified
3. Thickness of adhesive up to 10 mm
4. Easy to use and non-sag
5. Very low VOC

Areas of application

→ Intended use

Substrates:

- cement-based screeds and mortars
- cement-based plasters/renders
- concrete
- Biocem-based screeds
- cement-based self-levelling products

Materials:

- tiles
- terracotta
- ceramic mosaic
- red clay wire cut bricks

Uses:

- for floors and walls
- for internal use
- domestic applications
- commercial applications

Instructions for use

→ Preparation of the substrate

All surfaces must be dimensionally stable according to IS 1443-1972, leveled, cured, undamaged, compact, rigid, resistant, dry and free from any debonding agents and from damp rising. It is good practice to dampen highly absorbent concrete substrates or apply a coat of suitable primer.

→ Adhesive preparation

Mixing water:

- ≈ 6 - 7.2 litres per 30 kg bag
- ≈ 4 - 4.8 litres per 20 kg bag

→ Application

To guarantee maximum adhesion it is necessary to apply a sufficient layer of adhesive. Check samples to make sure the adhesive has been transferred to the back of the material.

Create elastic expansion joints:

- ≈ 10 m² in external applications,
- ≈ 25 m² in internal applications,
- every 8 metres in long, narrow applications.

Respect all structural, fractionizing and perimeter joints present in the substrates.

Special notes

→ Materials and special substrates

Marble, natural stones and recomposed materials that are subject to deformation or staining due to water absorption require a reactive adhesive.

Marble, natural stones and recomposed materials in general may have characteristics that vary even with reference to materials of the same chemical and physical nature. For this reason it is essential you consult Kerakoll India Helpline to request specific indications or to carry out a test on a sample of the material. Check for the presence of any really consistent traces of rock dust created during cutting, and remove them if found.

Do not use:

- on timber, metal, plastic or resilient materials, deformable substrates or subject to vibrations
- on substrates subject to vibrations
- on plasterboard and fibre-cement slabs
- on non-cured screeds, plaster/renders or concrete
- on plasterboard and fibre-cement slabs.

Certificates and marks



Technical Data compliant with Kerakoll Quality Standard		
Pack	20 kg and 30 kg bags	
Shelf life	≈ 12 months from production in the original packaging, protect from humidity	
Adhesive thickness	≤ 10 mm	
Temperature of the air, substrates and materials	from +5 °C to +35 °C	
Pot life at +27 °C	≈ 3 hr	
Open time at +27 °C (BIII tile)	≥ 15 min.	EN 12004
Foot traffic/grouting of joints at +35 °C (BIa tile)	≈ 24 hrs	EN 14411
Grouting in walls at +35 °C	≈ 18 hrs	EN 14411
Ready for use at +35 °C (BIa tile):		
- foot traffic	≈ 2 days	EN 14411
- heavy traffic	≈ 3 days	EN 14411
Consumption per mm of thickness	≈ 1.2 kg/m²	

Values taken at +23 °C, 50% R.H. and no ventilation. Data may vary depending on specific conditions at the building site, i.e.temperature, ventilation and absorbency level of the substrate and of the materials laid.

Performance		
VOC Indoor Air Quality (IAQ) - Volatile organic compound emissions		
Conformity	EC 1 plus GEV-Emicode	Cert. GEV 23204/11.01.02
HIGH-TECH		
Tensile adhesion strength (dry condition)	≥ 0.5 N/mm ²	IS 15477:2019
Shear adhesion (dry condition)	≥ 1 N/mm ²	IS 15477:2019
Vertical slip	≤ 0.5 mm	IS 15477:2019
Durability test:		
- adhesion after heat ageing	≥ 0.5 N/mm ²	EN 12004-2
- adhesion after water immersion	≥ 0.5 N/mm ²	EN 12004-2
- adhesion after freeze-thaw cycles	≥ 0.5 N/mm ²	EN 12004-2
Working temperature	from -30 °C to +80 °C	

Values taken at +27 °C, 65 ± 5% R.H. and no ventilation. Data may vary depending on specific conditions at the building site.

Warning

- Abide by any standards and national regulations

→ do not use the adhesive to correct substrate irregularities greater than 10 mm

→ lay and press tiles onto fresh adhesive, making sure it has not formed a surface skin

→ protect against direct rain and freezing for at least 24 hrs

→ the temperature, ventilation and absorption of the substrate and covering materials, may vary the adhesive workability and setting times
- use a toothed spreader suitable for the format of the tiles

→ use the floating and buttering method for all external laying

→ if necessary, ask for the safety data sheet

→ for any other issues, contact the Kerakoll India Helpline (Toll Free) 1800-200-6550 – info@kerakollindia.com

This information was last updated in May 2026; please note that additions and/or amendments may be made over time by KERAKOLL SpA; for the latest version, see www.kerakoll.com. KERAKOLL SpA shall therefore be liable for the validity, accuracy and updating of information provided only when taken directly from its institutional website. The technical data sheet given here is based on our technical and practical knowledge. As it is not possible for us to directly check the conditions of your building site and the execution of the work, this information represents general indications that do not bind Kerakoll in any way. Therefore, it is advisable to perform a preliminary test to verify the suitability of the product for your purposes.