

Addensante

Thixotropic agent for synthetic binding or finishing products.

Powder compound made up of polyethylene fibre fillers. Thickens and render thixotropic epoxy binders and structural supports in continuous 3-layer systems Cementoresina. Ideal to seal crazing, grout steps and fix edge beams and profiles.



1. Easy and fast to mix
2. Thickens without becoming heavy, guaranteeing flat, drip-free joints and finishing coats
3. Ideal to make epoxy binders thixotropic
4. Specific to render Floorzero structural finishing thixotropic

Areas of application

→ Use

Additive to thicken and render thixotropic:

- epoxy based products
- polyurethane products
- EP21
- Floorzero

Instructions for use

→ Preparation

The product is ready-to-use.

→ Application

After mixing together the epoxy resin components (A+B), or the structural supports, Floorzero, add Addensante under continual stirring until the compound is smooth and even. Add Addensante from 10 – 15% by weight to EP21 and from 3 – 5% by weight to Floorzero. The amount of Addensante must be adjusted according to the thixotropic level required.

Special notes

→ Addensante thickening agent must be incorporated in products to avoid the formation of dust. Avoid any contact with the respiratory system, skin and eyes. Wear rubber gloves, a protective face mask and professional goggles both while mixing and during use of the product.

If the product comes into contact with the skin, wash thoroughly with soap and water. See a doctor if there are any signs of allergy. Should the product come into contact with the eyes, rinse well with running water and see a doctor.

Certificates and marks



* Émission dans l'air intérieur Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

Technical Data compliant with Kerakoll Quality Standard	
Appearance	white powder
Pack	plastic bucket 1 kg
Apparent volumetric mass	104 kg/m³
Fibre length	0,10 – 0,25 mm
Shelf life	≈ 12 months from production in the original sealed packaging
Temperature range for application	from +10 °C to +30 °C
Coverage:	
- with EP21	10 – 15% by weight
- with Floorzero	3 – 5% by weight

Values taken at +20 °C, 65% R.H. and no ventilation. Data may vary depending on specific conditions at the building site.

Warning

- Abide by any standards and national regulations

→ use at temperatures between +5 °C and +30 °C

→ apply on dry substrates

→ do not add binders or additives

→ protect from direct sunlight and currents of air for the first 6 hours

→ do not apply on dirty or loose surfaces

→ dispose of as indicated in applicable legislation
- protect any surfaces and objects in the application area from accidental contact with the product

→ read the product safety data sheet before use

→ for any other issues, contact the Kerakoll Worldwide Global Service +39 0536 811 516 - globalservice@kerakoll.com



This information was last updated in September 2026; please note that additions and/or amendments may be made over time by KERAKOLL SpA; for the latest version, see www.kerakoll.com. KERAKOLL SpA shall therefore be liable for the validity, accuracy and updating of information provided only when taken directly from its institutional website. The technical data sheet given here is based on our technical and practical knowledge. As it is not possible for us to directly check the conditions in your building site and the execution of the work, this information represents general indications that do not bind Kerakoll in any way. Therefore, it is advisable to perform a preliminary test to verify the suitability of the product for your purposes.