

Oil-Pur

Treatment to protect hardwood floors.

Oil-Pur is both practical and easy-to-use for an antique-effect finish on wood floors of any type.



SLC
TECHNOLOGY

1. Two-coat finishing cycle
2. Intense colour-toning of wood
3. Compliant with
Directive 2004/42/EC

Areas of application

→ Use

High protection finish for:

- traditional wood floors
- prefinished wood floors
- wood floors to be restored
- bamboo floors

Interior wood floors in residential buildings.

Do not use in external applications; on wooden floors subject to prolonged or constant contact with water.

Instructions for use

→ Buff the hardwood floors until the surface is smooth, clean and free from oil, grease, wax, silicon and previous coats of varnish. Apply Aqua-Pur Flex (following the instructions on the data sheets) to fill cracks and irregularities. After $\approx$ 30-60 minutes, sand with sandpaper grain 100/120 from the range. Sand again using an Carboplus Sic 150 or 180 grain abrasive mesh disc for a better finish.

Carefully remove any dust created during sanding and wipe away any residues using a Pulex antistatic cloth, then apply Oil-Pur. The moisture content of the wood must be between 9% and 11%.

→ Preparation

The product is ready-to-use. Shake well before use and pour the product into a clean container. Wait 5 minutes before applying.

→ Application

Apply Oil-Pur using a Roller Classic and with a coverage of $\approx$ 80 – 100 ml/m². Wait approximately 6-8 hours for the product to fully dry, then sand evenly with a Carboplus Sic 220 abrasive mesh disc, carefully remove any dust created during sanding and wipe away any residue using a Pulex antistatic cloth, then apply the second coat of Oil-Pur.

→ Cleaning

Clean away any residue of Oil-Pur with turpentine before it hardens. Once hardened, Oil-Pur can only be removed mechanically. This product contains microplastics: do not release the product into the environment during use or disposal. Do not clean tools under running water. Do not pour product residues, water, or other washing solutions into household drains or sewers.

Special notes

- Allow product to reach room temperature before use.
- Use clean containers and tools.
- Once opened, the can must be used as quickly as possible.

- For an even finish, apply evenly in accordance with the recommended quantities.
- Maintenance of hardwood floors: wooden floors painted with Oil-Pur must be cared for periodically. Use Supersoap neutral detergent to clean the surface.

Abstract

Antique-effect finishing protection of the wooden floor will be provided using a single-component treatment with intense wood staining capacities, compliant with Directive 2004/42/CE, such as Oil-Pur by Kerakoll Spa, applied by roller in two coats of $\approx$ 80-100 ml/m² per coat.

Technical Data compliant with Kerakoll Quality Standard

Appearance	dark brown liquid
Pack	oilers 5 l
Shelf life	≈ 12 months from production in the original sealed packaging
Warning	protect from frost, avoid direct exposure to sunlight and sources of heat
Temperature range for application	from +10 °C to +30 °C
Shine factor:	
- Oil-Pur 10	≈ 10 gloss
- Oil-Pur 30	≈ 30 gloss
- Oil-Pur 60	≈ 60 gloss
- Oil-Pur 90	≈ 90 gloss
Waiting time:	
- for overlaying	≈ 8 hrs after sanding down
- for foot traffic	≈ 24 – 36 hrs
- for normal / intense foot traffic	≈ 7 – 10 days
Coverage	≈ 80 – 100 ml/m ² per coat

Values taken at +23 °C, 50% R.H. and no ventilation. Data may vary depending on specific conditions at the building site, i.e. temperature, ventilation and absorbency level of the substrate.

Warning

- Abide by any standards and national regulations
- check compatibility (colour, the content of resins, oils and other substances) with less common woods
- strong-coloured wood types and/or exotic woods with a high oil content (Ipe, Lapacho, Iroko, Mahoganies, etc.) can delay and/or inhibit drying and hardening of the product; it is therefore recommended, before applying the first coat, to rub the wood with a cloth soaked in Diluente Oil then leave the wood to dry and apply a very thin first coat, also ventilating the room well to encourage the drying process
- remove all residues of previous treatments to ensure an even finish
- always check room/ambient temperature and moisture content of wood
- protect from direct sunlight and air currents for the first 3 hours
- keep away from fire and sparks, do not smoke
- remains of product, tools, wood dust, cotton cloths, paper and similar products soaked in the liquid product and left in this state may ignite spontaneously; they must be damped down with water and left to dry in areas where there is no risk of combustion, before disposal
- if necessary, ask for the safety data sheet
- for any other issues, contact the Kerakoll Worldwide Global Service +39 0536 811 516 - globalservice@kerakoll.com



This information was last updated in September 2026; please note that additions and/or amendments may be made over time by KERAKOLL SpA; for the latest version, see www.kerakoll.com. KERAKOLL SpA shall therefore be liable for the validity, accuracy and updating of information provided only when taken directly from its institutional website. The technical data sheet given here is based on our technical and practical knowledge. As it is not possible for us to directly check the conditions in your building site and the execution of the work, this information represents general indications that do not bind Kerakoll in any way. Therefore, it is advisable to perform a preliminary test to verify the suitability of the product for your purposes.