


Geosteel G3300

Unidirectional, extra-high strength galvanized steel fibre sheets, made of steel micro-cords, fixed to a fibreglass micromesh. Geosteel G3300 is specific for use in structural reinforcements in combination with Geolite Gel organic matrix.

Thanks to its characteristics GeoSteel G3300 is easy to shape and has excellent installation and durability properties. Geosteel G sheets guarantee superior properties than traditional carbon-glass-aramide fibre sheets, and are particularly effective in various structural strengthening and anti-seismic improvement or compliance operations, as well as in the creation of connection systems.



1. High durability thanks to the special steel wire galvanisation process
2. Certified for use in structural strengthening in combination with Geolite Gel epoxy mineral matrix
3. Can be tensioned for structural strengthening and active devices
4. Easy to shape using Geosteel pneumatic bender

Areas of application

→ Intended use

- Static and seismic upgrade or compliance retrofit of structural elements in reinforced concrete, prestressed reinforced concrete, masonry, wood and steel
- Compressive and flexural stress, shear, and confinement reinforcing for partitions in reinforced concrete, prestressed reinforced concrete and wall panels

- Confinement and banding of reinforced concrete, prestressed reinforced concrete or masonry structural elements
- Consolidation of masonry arches, vaults and domes
- Flexural strengthening for timber elements
- Flexural strengthening for steel girders

Instructions for use

→ Preparation

The Geosteel G3300 sheet, in extra-high strength galvanized steel fibre is ready-to-use.

The sheet can be cut at right angles to the cords with manual or electric shears, or parallel with the cords using a normal box cutter. The sheet, cut into strips even just a few cm wide and a number of metres long, ensures perfect stability without in any way compromising the workability of the material and its application.

→ Preparation of substrates

The substrate must be properly prepared and cleaned, always in accordance with the instructions dictated by the construction supervisor

In the case of substrates that are not degraded, prepare the surfaces as indicated in the technical data sheet for Geolite Gel.

When the substrate is clearly deteriorated, uneven, or damaged by significant events, proceed as follows, always in accordance with the construction supervisor:

Substrates in reinforced concrete or prestressed reinforced concrete:

- Thorough removal of weakened concrete if necessary, through mechanical scarification or hydro-demolition, making sure to roughen the substrate to a depth of at least 5 mm, equal to level 8 of the "Test kit for preparation of reinforced concrete and masonry substrates";
- Removal of rust, if any, from reinforcing bars, which must be cleaned by brushing (manual or mechanical) or sandblasting;
- Monolithic reconstruction or smoothing of the section, if needed, using geo-mortar based on a mineral geo-binder such as Geolite.
- Before applying the strengthening system with an organic matrix, the substrate must be dry and free of humidity and with a roughness of at least 0.5 mm, equal to level 5 of the "Test Kit for preparation of reinforced concrete and masonry substrates" (follow the instructions on the Geolite Gel data sheet).

→ Application

The execution of the structural strengthening Steel Reinforced Polymer (a combination of Geosteel G sheets and Geolite Gel epoxy mineral matrix), after having appropriately evened out the surface must be carried out using Geolite, for reinforced concrete substrates, using Geocalce G Antisismico or Geocalce F Antisismico for masonry substrates. Take care to allow the geo-mortar to cure for a period of time sufficient to guarantee a suitable humidity of the substrate before applying Geolite Gel. Before applying the first layer of Geolite Gel, the substrate must be clean, dry, free from damp and roughened by sanding or mechanical scarification to a depth of at least 0.5 mm, equal to level 5 of the "Test Kit for preparation of reinforced concrete and masonry substrates". The first layer of adhesive must have an average thickness of approx. 2-3 mm. Then apply the ultra-high strength, galvanized steel fibre Geosteel G3300 sheet to the still wet matrix. Take care that the mesh is perfectly embedded in the matrix layer, applying firm pressure with a steel spreader or roller. Make sure that the netting protrudes from the cords, in order to ensure excellent adhesion between the first and second matrix layers. At longitudinal joint points, overlap two layers of galvanized steel fibre sheet by at least 20 cm. Finally, apply a fresh on fresh final protective smoothing in order to completely incorporate the reinforcement and seal any underlying voids for a total thickness of the reinforcement of \approx 3 - 4 mm. If there are additional layers after the first, proceed with laying of the second layer of steel fibre over the matrix while it is still wet. In the event that the system must be plastered or concealed by smoothing, we recommend that while the resin is still wet that you apply a spray of mineral quartz to provide better adhesion for subsequent layers.

If the strengthening system is installed in especially aggressive environments, or you otherwise wish to ensure additional protection beyond that already provided by the matrix, it is recommended to apply Kerakover Acrilex Flex.

Instructions for use

If the works are in permanent or occasional contact with liquids, it is recommended to get in touch with the Kerakoll technical department to arrange the most suitable protection system.

For technical specifications, the application and preparation of the matrix, and the most suitable protective system, please consult the relevant technical data sheets.

Abstract

SRP-Geolite Gel & Geosteel G3300

Execution of repair, structural strengthening, improvement or seismic upgrade of reinforced concrete and prestressed reinforced concrete elements and structures using an organic matrix composite system, SRP (Steel Reinforced Polymer), CE-marked, with European Technical Assessment (ETA) pursuant to art. 26 of EU Regulation No. 305/2011 and international certificate of proven validity. SRP composed of unidirectional, extra-high strength galvanized steel fibre sheet, made of steel micro-cords compliant with standard ISO 16120-1/4 2017 fixed to a fibreglass micromesh, net weight of $\approx 3300 \text{ g/m}^2$ – such as Geosteel G3300 by Kerakoll Spa – with the sheet featuring the following certified technical characteristics: tensile strength, characteristic value $> 3000 \text{ MPa}$; modulus of elasticity $> 190 \text{ GPa}$; ultimate break warp $> 1.5\%$; actual area of a cord 3×2 (5 wires) = 0.538 mm^2 ; no. cords per cm = 7.09, with wire winding at high torque angle, compliant with standard ISO/DIS 17832; equivalent thickness of the sheet = 0.381 mm , Geosteel G3300 impregnated with Geolite Gel by Kerakoll Spa, epoxy mineral adhesive in gel form, for structural bonding of galvanized steel fibre sheets or other types of composite materials in general, CE-marked and compliant with the performance requirements indicated in Standards EN 1504-4 and EN 1504-6 for bonding structural elements and following the guidelines of CNR-DT 200 RI/2013, without the need for an adhesion primer, solvent-free, with very low volatile organic compound emissions. To be applied directly to the structure requiring strengthening.

The procedure is conducted as follows:

1. Any restoration of degraded, weakened, non-cohesive, or non-planar surfaces, using Geolite by Kerakoll Spa and in any case as prescribed and approved by the construction supervisor;
2. Preparation of the substrate for application of the first layer of Geolite Gel, the substrate must be adequately roughened by sanding or mechanical scarification, taking care to guarantee a roughness of at least 0.5 mm (equal to level 5 of the Test Kit for preparation of reinforced concrete and masonry), clean and free from damp;
3. Application of a first layer with an average thickness of $\approx 2\text{-}3 \text{ mm}$ of epoxy mineral matrix Geolite Gel by Kerakoll Spa;
4. While the epoxy mineral adhesive is still wet, lay the ultra-high strength galvanized steel fibre Geosteel G3300 sheet by Kerakoll Spa. By pressing firmly with a smooth spreader or metal roller, make sure that the sheet is completely impregnated and avoid allowing any gaps or air bubbles to form, because these can compromise the adhesion of the sheet to the matrix or the substrate;
5. Working fresh on fresh, apply the second layer of epoxy mineral matrix Geolite Gel by Kerakoll Spa, until the reinforcing sheet is fully incorporated and any underlying voids are filled, giving an overall reinforcement thickness of $\approx 3\text{-}4 \text{ mm}$;
6. Repeat steps (4) and (5) if necessary for all subsequent reinforcing layers called for by the design;
7. Any insertion of thread connectors made from unidirectional, extra-high strength galvanized steel fibre sheets, after preparation of the entrance bore, with a size suited to the nature of the connector to be fitted; after preparation of the steel connector by cutting, creating "threads" and final rolling of the steel-fibre sheet, locking it in place with a plastic tie; after insertion of the pre-formed connector into the bore with final, low pressure injection of Epofix epoxy anchoring agent or Geolite Gel epoxy mineral matrix.

delivery and installation of all the materials described above as well as everything else required to finish the job is included. The following are excluded: removal of any existing plaster/render, restoration of degraded areas and repair of the substrate; connectors, their injection and all the costs and charges required to create them; material acceptance tests; pre- and post-procedure testing, all aids required to perform the work.

The price is by unit of reinforcing surfaces actually laid, including overlaps.

Certificates and marks



CE-marked in combination with Geolite Gel and Epofix for concrete structures

Technical Data compliant with Kerakoll Quality Standard

Values are for non-impregnated sheet

Cord 3x2 obtained by joining 5 filaments, of which 3 straight and 2 wrapped with a high torque angle

- actual area of a cord 3x2 (5 wires)	A_{cord}	0,538 mm ²
- n° cords/cm		7.09 cords/cm
- mass (inclusive of thermal welding)		≈ 3300 g/m ²
- tensile breaking load of a cord		> 1500 N
- tensile strength of the sheet, characteristic value	σ_{sheet}	> 3000 MPa
- tensile strength by unit of width		> 10.67 kN/cm
- normal elastic modulus of sheet, average value	E_{sheet}	> 190 GPa
- break warp of the sheet, characteristic value	ϵ_{sheet}	> 1.5%
- equivalent thickness	t_i	≈ 0.381 mm
Pack		20 m rolls (h 30 cm)
Weight of 1 roll		≈ 20 kg including packaging

Performance					
Geosteel SRP system – ETA n° 18/0314					
SRP – Geolite Gel & Geosteel G3300					
Performance characteristic	Test Method		Geosteel SRP G3300 (1 layer) system performance	Geosteel SRP G3300 (3 layers) system performance	Project data according to CNR-DT 200 R1/2013
Tensile strength (characteristic value)	EN 2561	σ_{SRP}	2977 MPa	2709 MPa	2700 MPa
Modulus of elasticity (average value)	EN 2561	E_{SRP}	216 GPa	212 GPa	210 GPa
Ultimate elongation (average value)	EN 2561	ϵ_{SRP}	1,87%	1.79%	1.80%
Lap tensile strength ¹ (characteristic value)	EN 2561	σ_{lap}	1086 MPa	NPD	-
Tensile strength on bent fabric (characteristic value)	EN 2561	$\sigma_{u,f,bent}$	NPD	NPD	-
Glass transition temperature	EN 12614	T_g	+60 °C	+60 °C	-
Substrate adhesion²					
Pull-off strength (characteristic value)	EN 1542	f_h	2,7 MPa	NPD	-
Single-lap shear test (characteristic value)	Annex B EAD 340210-00-0104	σ_{deb}	614 MPa	NPD	-
Pull-out from substrate (Geolite Gel, average value)	Annex C EAD 340210-00-0104	$\sigma_{pull-out}$	1677 MPa	NPD	-
Pull-out from substrate (Epofix, average value)	Annex C EAD 340210-00-0104	$\sigma_{pull-out}$	1423 MPa	NPD	-
Installation conditions					
Maximum temperature (air and substrate)	-	-	< +35 °C		
Minimum temperature (air and substrate)	-	-	> +5 °C		
Relative air humidity	-	-	20 – 90%		
Moisture of the substrate (gluing surface) ³	-	-	< 5%		
Service conditions					
Maximum temperature (air and substrate)	-	-	< +45 °C		
Minimum temperature (air and substrate)	-	-	> -25 °C		
Relative air humidity	-	-	irrelevant		
Contact with water ⁴	-	-	occasional		
Reaction to fire ⁵	EN 13501-1	-	Class D-s2, d0		

In the presence of installation and working temperatures outside the limits indicated above, contact the Kerakoll technical department to provide for suitable protective systems for application and operation of the Geosteel SRP reinforcement system.

¹ Overlap length $l_{lap} = 200$ mm.

² Tests carried out on concrete prisms with compressive strength $f_b = 57.5$ MPa.


³ In the presence of a wet support, wait for it to completely dry or facilitate its drying before applying the product.

⁴ In the event of permanent contact with liquids, contact the Kerakoll technical department to provide for the most suitable protective system.

⁵ In case of exposure to fire load, or fire resistance, protect the Geosteel SRP reinforcement system by means of an appropriate REI certified system. The Geosteel SRP system has no fire resistance.

Warning

- Abide by any standards and national regulations
- when handling the sheet wear protective clothing and goggles, and follow the instructions regarding methods for applying the material
- contact with the skin: no special measures required
- storage on the work site: store under cover in a dry place, well away from substances that might damage it or its ability to adhere to the chosen matrix
- the product is an item according to the definitions of the EC Regulation No. 1907/2006 and therefore does not require a Safety Data Sheet
- for any other issues, contact the Kerakoll Worldwide Global Service +39 0536 811 516 - globalservice@kerakoll.com



This information was last updated in May 2026; please note that additions and/or amendments may be made over time by KERAKOLL SpA; for the latest version, see www.kerakoll.com. KERAKOLL SpA shall therefore be liable for the validity, accuracy and updating of information provided only when taken directly from its institutional website. The technical data sheet given here is based on our technical and practical knowledge. As it is not possible for us to directly check the conditions of your building site and the execution of the work, this information represents general indications that do not bind Kerakoll in any way. Therefore, it is advisable to perform a preliminary test to verify the suitability of the product for your purposes.