

# Klima Light

Low-density ETICS adhesive-finishing product for the laying of heat-insulating panels.

Low-density adhesive&finishing product for insulation, specifically intended for laying and finishing thermal insulation panelling systems on heat-insulating panels for ETICS use made of extruded polystyrene, expanded polystyrene and polystyrene foam for specific use in ETICS plinths, polyurethane, phenolic resin, cork, mineral and glass wool, wood fibre, aerogel on concrete, brick, cement-based plaster/render, mineral and cement-based finishing products. White. For internal and external use.

1. Superior fluidity, easy and light to spread
2. Extremely high coverage; up to 50% more compared to traditional adhesive&finishing products
3. Calibrated grading; fine aesthetic finish compared to standard low-density products
4. High thicknesses can be applied; thixotropic, it does not drip nor shrink
5. Product in the Klimaexpert ETA EPS system
6. Suitable for Klimaexpert Fire Protection kits



---

## Areas of application

### → Use

- Bonding and finishing of panelling systems for:
- Klimaexpert ETA EPS Systems with European Technical Approval according to EAD 040083-00-0404
  - Klimaexpert Fire Protection Kit
  - external insulation
  - internal insulation

For internal and external use on heat sealed external insulating systems (ETICS) made of extruded polystyrene, expanded polystyrene and polystyrene foam for ETICS specific use, polyurethane, phenolic resin, cork, mineral and glass wool, wood fibre, aerogel on concrete, brick, cement-based plaster/render, mineral and cement-based finishing products.

Do not use on walls coated with gypsum or ready-mixed gypsum-based plasters; to apply ceramic or natural stone tiles; on wooden or metal supports.

---

## Instructions for use

### → Preparation of substrates

The substrate must be perfectly even, solid (i.e. free of loose or easily removable debris), dimensionally stable, clean and dry. Substrates that are not compact must be treated in advance with Universal Wall Primer or Rasobuild Consolidante stabilizing consolidant. Check that there are no traces of de-bonding agent on the concrete.

Any uneven areas should be corrected in advance with products in the Geolite or Geocalce range. Do not apply on substrates when the temperature is above +30 °C.

### → Preparation

Klima Light is prepared by mixing 20 kg of powder with the amount of water indicated on the bag. The mixture is obtained by pouring water into the clean container and then gradually adding the powder. The mixing process can be performed in a horizontal cement mixer or in a bucket (working manually or with a low-rev, mechanical stirring device) until a smooth and lump-free mortar is obtained.

### → Application

As an adhesive: according to the irregularity of the substrate, Klima Light can be applied as an external rim with central spots or using a suitable toothed spreader to form a solid bed directly on the panel. The slabs must be pressed firmly onto the support so as to distribute the adhesive as evenly as possible and thus guarantee total adhesion of the slab itself.

Laying and any adjustment of the panels must always be carried out when the adhesive is fresh and just laid: any movement or adjustment of the panels once drying has started may cause the adhesion to be poor or the panels to come loose. As a finishing product: when used as a finishing product on heat sealed panels, a first coat of Klima Light is applied in an even layer using a smooth spreader; a suitable mesh for ETICS use should then be sunk into the layer while it is still wet, pressing it with the spreader. Once the first coat has dried, apply a second coat over the top, covering the mesh completely to create a finished surface which, on drying, can be used to lay high-thickness decorative coverings. On completion, the panels must be protected from rain for at least 48 hours. Klima Light can be applied by spraying using plastering machines. For applications in heat-insulating systems, refer to the national regulations.

### → Cleaning

Residual traces of Klima Light can be removed from tools with plain water before the product has hardened.

## Special notes

- When laying heat-insulating panels, always follow the indications provided by the manufacturer of the panels themselves.
- Laying on gypsum: on walls coated with gypsum, scagliola or ready-to-use gypsum-based plasters the substrate must be treated with Universal Wall Primer or Rasobuild Consolidante before applying Klima Light.

## Certificates and marks



\* Émission dans l'air intérieur Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

## Abstract

*Application and finishing of the thermal insulation panels, with insertion of alkali-resistant, glass fibre mesh for ETICS use by Kerakoll Spa between the two layers, is to be carried out on a substrate that is even, solid, clean and dry. The panels must first be bonded and then surface finished using low-density mineral single-component adhesive&finishing product, suitable for the laying and the finishing of all types of heat-insulating panels for ETICS use on absorbent substrates, such as Klima Light by Kerakoll Spa, specific for the creation of insulation panelling systems. Klima Light adhesive&finishing product forms part of the Klimaexpert ETA EPS systems with European Technical Approval - ETA - under EAD 040083-00-0404. Coverage will be  $\approx 2 - 3.5 \text{ kg/m}^2$  for bonding and  $\approx 1 \text{ kg/m}^2$  for the finishing coat per mm of thickness.*

<b>Technical Data compliant with Kerakoll Quality Standard</b>		
Appearance	white pre-mixed	
Apparent density of dry, hardened product	1.01 kg/dm <sup>3</sup>	EN 1015-10
Mineralogical nature of inert material	silicate – crystalline carbonate	
Nominal Grading	≈ 0 – 1200 µm	EN 1015-1
Ash content at +450 °C	98.0%	EAD 040083-00-0404
Ash content at +900 °C	67.0%	EAD 040083-00-0404
Water retention	> 91%	EAD 040083-00-0404
Shelf life	≈ 12 months from production in the original sealed packaging, protect from humidity	
Pack	20 kg bags	
Mixing water	≈ 5.8 l / 1 bag 20 kg	
Specific weight of the mixture	≈ 1.2 kg/dm <sup>3</sup>	EN 1015-6
Pot life	≥ 5 hrs	
Temperature range for application	from +5 °C to +30 °C	
Maximum thickness obtainable as adhesive	≤ 20 mm	
Maximum thickness obtainable when used as a finishing product	≤ 15 mm (two coats with an inserted insulation panelling system mesh)	
Coverage:		
- as an adhesive	≈ 2 – 3.5 kg/m <sup>2</sup>	
- as a finishing coat	≈ 1 kg/m <sup>2</sup> per mm of thickness	

Values taken at +23 °C, 50% R.H. and no ventilation. Data may vary depending on specific conditions at the building site.

**Performance****VOC Indoor Air Quality (IAQ) - Volatile organic compound emissions**

Conformity	EC 1 plus GEV-Emicode	GEV Certified 10268/11.01.02
------------	-----------------------	---------------------------------


**HIGH-TECH**

Thermal conductivity ( $\lambda_{10, \text{dry}}$ )	0.27 W/(m K)	EN 12664
Specific thermal capacity (c)	0.74 kJ/(kg K)	ISO 11357-4
Adhesion to concrete after 28 days	$\geq 0.8$ N/mm <sup>2</sup>	EAD 040083-00-0404
Adhesion between adhesive and EPS	$\geq 0.1$ N/mm <sup>2</sup> (EPS cohesive tear)	EAD 040083-00-0404
Water capillary absorption	0.39 kg/m <sup>2</sup>	EAD 040083-00-0404
Compressive strength	$\approx 4$ MPa	EN 1015-11
Resistance to the diffusion of water vapour	$\mu 11$	EN 1015-19
Flexural strength	$\approx 2$ MPa	EN 1015-11
Reaction to fire	class A1	EN 13501-1
Working temperature	from -15 °C to +80 °C	

Values taken at +23 °C, 50% R.H. and no ventilation. Data may vary depending on specific conditions at the building site.

## Warning

- Abide by any standards and national regulations
- use at temperatures between +5 °C and +30 °C
- only use water when mixing up the powder: do not use latex or other additives
- provide suitable mechanical hooks in compliance with current regulations
- do not use the adhesive to correct substrate irregularities
- do not move the panels once the adhesive has started to harden
- do not lay on gypsum, metal or wood
- do not lay on damp substrates
- protect the coated surfaces from rain for at least 48 hours
- if necessary, ask for the safety data sheet
- for any other issues, please contact the Kerakoll Worldwide Global Service +39 0536 811 516



This information was last updated in March 2026; please note that additions and/or amendments may be made over time by KERAKOLL SpA; for the latest version, see [www.kerakoll.com](http://www.kerakoll.com). KERAKOLL SpA shall therefore be liable for the validity, accuracy and updating of information provided only when taken directly from its institutional website. The technical data sheet given here is based on our technical and practical knowledge. As it is not possible for us to directly check the conditions of your building site and the execution of the work, this information represents general indications that do not bind Kerakoll in any way. Therefore, it is advisable to perform a preliminary test to verify the suitability of the product for your purposes.