

**TEST REPORT****395700 / 1**Revision: 1  
Date of sample receipt: 07/07/25  
Date of test: 23/07/25  
Date of issue: 25/08/25

Sample name: EXENCE QUARTZ STONE

KERAKOLL S.P.A.  
VIA DELL'ARTIGIANATO 9  
41049 SASSUOLO (MO)  
ITALIA**Determination of Metals CAM - PTP 174 Rev. 2 del 2020****OBJECTIVE**

Determinations of dangerous substances in material  
to point 2.5 of the CAM (Minimum Environmental Criteria)  
for awarding the design and execution of construction work

**MATERIAL**

Paints and coatings (2.5.13)

**SAMPLE PREPARATION**

The material has been digested with acid mixture

**USED TECHNIQUE**

ICP-OES: Inductively Coupled Plasma - Optical Emission Spectroscopy

UV-VIS: Ultraviolet Visible Emission Spectroscopy

**TEST RESULTS**


The result is expressed on the dried sample

ANALYZED METALS	VALUE mg/kg	Note
As	< 10	< 100 (*)
Cd	< 10	
Cr (VI)	< 10	
Hg	< 10	
Pb	< 10	
Se	< 10	

(\*)The material complies with point b of paragraph 2.5.13 Minimum Environmental Criteria (CAM)  
referred to the Ministerial Decree dated 23/06/2022 n. 256 G.U. n. 183 dated 6/08/2022 - effective from 4/12/2022

This document replaces the previous one with revision number 0 and with date of issue 23/07/25. Applied changes: sample name on customer request.

This test report is part of a PDF file digitally signed by Daniele Bergamasco.

The deputy director  
Dr. Daniele Bergamasco  


Chemical Testing Manager  
Dr. Daniele Bergamasco  
Chemist  
Association of Chemists and  
Physicists  
Regional registration No. 287

The sample name and, when relevant, its description, are given by the orderer, and CATAS does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise required by standards and technical specifications or agreed with the customer, any declarations of conformity made by CATAS are based on the comparison between results and reference values, where the confidence intervals of the measures are not taken into account. Unless otherwise stated, sampling is made by the customer; in this case the test results are referred to the sample as received.