

Ghiaia 3.6

Gravel with 3-6 mm grading curve.

Ghiaia 3.6 is a washed and selected fine concrete aggregate with grading curve, compliant with EN 12620, suitable for the preparation of fluid mortars and fine-grain concretes, compliant with EN 1504-3.



1. Optimises the grading curve of the mortar according to the thickness of application
2. Excellent mixing properties
3. Excellent adhesion to hydraulic binders

Areas of application

→ Use
Washed and selected fine concrete aggregate with grading curve from 3 to 6 mm, suitable for the preparation of fluid and self-compacting mortars, compliant with the requirements of

Standard EN 1504-3. For applications involving large application thicknesses, add Ghiaia 3.6 gravel in a ratio of approximately 25-40% of the weight of fluid mortars from the Geolite and Metric ranges.

Certificates and marks



Technical Data compliant with Kerakoll Quality Standard	
Appearance	washed fine concrete aggregate
Shelf life	unlimited
Pack	25 kg bags
Granulometry/grain size	3 – 6 mm
Density of granules (Mg/m³)	2.65
Long-lasting resistance to alkali-silica reaction	RA1

Warning

- Abide by any standards and national regulations
- use in the recommended dosages
- mix until a smooth mixture is obtained
- if necessary, ask for the safety data sheet
- for any other issues, contact Kerakoll Technical Customer Service:
+ 39 0536.811.516
www.kerakoll.com/contatti



This information was last updated in May 2026; please note that additions and/or amendments may be made over time by KERAKOLL SpA; for the latest version, see www.kerakoll.com. KERAKOLL SpA shall therefore be liable for the validity, accuracy and updating of information provided only when taken directly from its institutional website. The technical data sheet given here is based on our technical and practical knowledge. As it is not possible for us to directly check the conditions of your building site and the execution of the work, this information represents general indications that do not bind Kerakoll in any way. Therefore, it is advisable to perform a preliminary test to verify the suitability of the product for your purposes.