

Klima Light Calce

Low-density ETICS adhesive-finishing product with NHL lime for the laying of mineral and natural heat-insulating panels.

Lime-based, low-density, mineral Adhesive&Finishing product for insulation, specifically intended for the laying and finishing of thermal insulation panelling systems such as mineral and glass wool, wood fibre, cork, calcium silicate hydrates on concrete, brick, cement-based plaster/render, mineral and cement-based finishing products. Beige. For internal and external use.



1. Based on natural hydraulic lime NHL
2. Maximum breathability to water vapour
3. High wettability even on long-fibre insulating panels
4. Excellent workability: superior fluidity finishing product, easy and light to spread
5. Extremely high coverage; up to 50% more in finishing compared to traditional adhesive&finishing products
6. Can be applied using plastering machines
7. Euroclass A1 reaction to fire, thanks to the low-density mineral inert material
8. Product in the Klimaexpert ETA MW system
9. Suitable for Klimaexpert Fire Protection kits

kerakoll

Areas of application

→ Use

- Bonding and finishing of panelling systems for:
- Klimaexpert ETA MW with European Technical Assessment (ETA) according to EAD 040083-00-0404
 - external insulation
 - internal insulation
 - Klimaexpert Fire Protection Kit

Internal and external use on heat sealed insulating systems (ETICS) such as mineral and glass wool, wood fibre, cork, calcium silicate hydrates on concrete, brick, cement-based plaster/render, mineral and cement-based finishing products

Do not use on walls coated with gypsum or ready-mixed gypsum-based plasters; to apply ceramic or natural stone tiles; on wooden or metal supports.

Instructions for use

The instructions for use refer, where required, to the Italian Technical Report UNI / TR 11715 "Heat-insulating products for buildings - Design and installation of external heat-insulating systems (ETICS)".

→ Preparation of substrates (UNI / TR 11715 - paragraph 9)

The substrate must be perfectly even, solid (i.e. free of loose or easily removable debris), dimensionally stable, clean and dry. Substrates that are not compact must be treated in advance with Universal Wall Primer or Rasobuild Consolidante stabilizing consolidant. Check that there are no traces of de-bonding agent on the concrete.

Any uneven areas should be corrected in advance with products in the Geolite or Geocalce range. Do not apply on substrates when the temperature is above +30 °C.

→ Preparation

Klima Light Calce is prepared by mixing 20 kg of powder with the amount of water indicated on the bag. The mixture is obtained by pouring water into the clean container and then gradually adding the powder. The mixing process can be performed in a horizontal cement mixer or in a bucket (working manually or with a low-rev, mechanical stirring device) until a smooth and lump-free mortar is obtained.

→ Application (UNI / TR 11715 - paragraph 9)

As an adhesive: According to the evenness of the substrate, Klima Light Calce can be applied as an external rim with three central spots or full-bed laying directly on the panel, using a suitable toothed spreader. The slabs must be pressed firmly onto the support so as to distribute the adhesive as evenly as possible and thus guarantee total adhesion of the slab itself.

Laying and any adjustment of the panels must always be carried out when the adhesive is fresh and just laid: any movement or adjustment of the panels once drying has started may cause the adhesion to be poor or the panels to come loose. As a finishing product: When used as a finishing product on heat sealed panels, a first coat of Klima Light Calce is applied in an even layer using a smooth spreader; a suitable mesh for ETICS use should then be sunk into the layer while it is still wet, pressing it with the spreader. Once the first coat has dried, apply a second coat over the top, covering the mesh completely to create a finished surface which, on drying, can be used to lay high-thickness decorative coverings. On completion, the panels must be protected from rain for at least 48 hours. Klima Light Calce can be applied by spraying using plastering machines.

→ Cleaning

Residual traces of Klima Light Calce can be removed from tools with plain water before the product has hardened.

Special notes

→ When laying heat-insulating panels, always follow the indications provided by the manufacturer of the panels themselves.

→ Laying on gypsum: on walls coated with gypsum, scagliola or ready-to-use gypsum-based plasters the substrate must be treated with Universal Wall Primer or Rasobuild Consolidante before applying Klima Light Calce.

Certificates and marks



* Émission dans l'air intérieur Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).

Abstract

Application and finishing of the thermal insulation panels, with insertion of alkali-resistant, glass fibre mesh for ETICS use by Kerakoll Spa between the two layers, is to be carried out on a substrate that is even, solid, clean and dry. The panels must first be bonded and then surface finished using a lime-based, low-density, mineral, single-component Adhesive&Finishing product, suitable for the laying and the subsequent finishing of all types of heat-insulating panels for ETICS use on absorbent substrates, such as Klima Light Calce by Kerakoll Spa, specific for the creation of insulation panelling systems and meeting the requirements of the European Assessment Document EAD 040083-00-0404 for insulation with panelling systems. Coverage will be $\approx 2-3.5 \text{ kg/m}^2$ for bonding and $\approx 0.95 \text{ kg/m}^2$ for the finishing coat per mm of thickness.

Technical Data compliant with Kerakoll Quality Standard

Appearance	beige pre-mixed	
Apparent density of dry, hardened product	1.05 kg/dm^3	EN 1015-10
Mineralogical nature of inert material	silicate – crystalline carbonate	
Nominal Grading	$\approx 0 - 1200 \mu\text{m}$	EN 1015-1
Ash content at +450 °C	96.7%	EAD 040083-00-0404
Ash content at +900 °C	70.2%	EAD 040083-00-0404
Water retention	> 90%	EAD 040083-00-0404
Shelf life	≈ 12 months from production in the original sealed packaging, protect from humidity	
Pack	20 kg bags	
Mixing water	$\approx 6.4 \text{ l} / 1 \text{ bag } 20 \text{ kg}$	
Specific weight of the mixture	$\approx 1.2 \text{ kg/dm}^3$	EN 1015-6
Pot life	≥ 5 hrs	
Temperature range for application	from +5 °C to +30 °C	
Maximum thickness obtainable as adhesive	$\leq 20 \text{ mm}$	
Maximum thickness obtainable when used as a finishing product	$\leq 15 \text{ mm}$ (two coats with an inserted insulation panelling system mesh)	
Coverage:		
- as an adhesive	$\approx 2 - 3.5 \text{ kg/m}^2$	
- as a finishing coat	$\approx 0.95 \text{ kg/m}^2$ per mm of thickness	

Values taken at +23 °C, 50% R.H. and no ventilation. Data may vary depending on specific conditions at the building site.

Performance**VOC Indoor Air Quality (IAQ) - Volatile organic compound emissions**

Conformity	EC 1 plus GEV-Emicode	Cert. GEV 13369/11.01.02
------------	-----------------------	--------------------------


HIGH-TECH

Thermal conductivity ($\lambda_{10, dry}$)	0.28 W/(m K)	EN 12664
Specific thermal capacity (c)	0.7 kJ/(kg K)	ISO 11357-4
Adhesion to concrete after 28 days	≥ 0.8 N/mm ²	EAD 040083-00-0404
Adhesion between adhesive and MW	≥ 0.01 N/mm ² (MW cohesive tear)	EAD 040083-00-0404
Compressive strength	≈ 8 MPa	EN 1015-11
Resistance to the diffusion of water vapour	$\mu 10$	EN 1015-19
Water capillary absorption	0.35 kg/m ²	EAD 040083-00-0404
Flexural strength	≈ 3 MPa	EN 1015-11
Reaction to fire	class A1	EN 13501-1
Working temperature	from -15 °C to +80 °C	

Values taken at +23 °C, 50% R.H. and no ventilation. Data may vary depending on specific conditions at the building site.

Warning

- Abide by any standards and national regulations
- use at temperatures between +5 °C and +30 °C
- only use water when mixing up the powder: do not use latex or other additives
- provide suitable mechanical hooks in compliance with current regulations
- do not use the adhesive to correct substrate irregularities
- do not move the panels once the adhesive has started to harden
- do not lay on gypsum, metal or wood
- do not lay on damp substrates
- protect the coated surfaces from rain for at least 48 hours
- if necessary, ask for the safety data sheet
- for any other issues, contact Kerakoll Technical Customer Service:
+ 39 0536.811.516
www.kerakoll.com/contatti



This information was last updated in March 2026; please note that additions and/or amendments may be made over time by KERAKOLL SpA; for the latest version, see www.kerakoll.com. KERAKOLL SpA shall therefore be liable for the validity, accuracy and updating of information provided only when taken directly from its institutional website. The technical data sheet given here is based on our technical and practical knowledge. As it is not possible for us to directly check the conditions of your building site and the execution of the work, this information represents general indications that do not bind Kerakoll in any way. Therefore, it is advisable to perform a preliminary test to verify the suitability of the product for your purposes.