


Glass Net A305

Pre-formed, glass fibre corner mesh for CRM strengthening.

GFRP Glass Net A305 is a component of the CRM system to be combined with lime- or cement-based mortars.



1. Certified for CRM structural strengthening
2. Excellent tensile strength
3. High level of durability
4. Easy to install
5. For the strengthening of masonry and concrete structures

Areas of application

→ Intended use:

- Static and seismic upgrade or improvement of masonry and concrete structural elements by using the CRM reinforced plaster/render technique in combination with meshes from the Glass Net range, Glass Connect L grouted with Resinglass or Steel Dryfast helical bars and lime- or cement-based mortars

- Compressive and flexural stress and shear for wall panels

Instructions for use

→ Preparation

Glass Net A305 is ready to use and can be easily cut using shears or a sander. Its weave guarantees stability and ease of installation.

→ Preparation of substrates

The substrate must be meticulously prepared and cleaned in accordance with the technical data sheet of the chosen mortar: Geocalce G Antisismico, Biocalce Muratura, Geolite, Metric R3 Tixo or Metric R4 Tixo.

For applications on masonry, it is necessary:

- remove all finishing coats until the masonry is exposed;
- remove all weakened parts and inconsistent rendering mortars until a solid, resistant substrate is obtained; roughen it by mechanical scarification or hydro-demolition to a depth of at least 5 mm, equivalent to level 8 of the Test kit for preparation of reinforced concrete and masonry substrates;
- repair any missing parts of the masonry using fragment-filling or break-fill techniques;
- to saturate with water until the substrate is saturated yet with no excess water on the surface;
- on dusty substrates or substrates that are not compact, to apply Primer Uni diluted 1:4 using water until fully saturated
- on strongly uneven substrates, a layer of levelling mortar can be applied.

→ Application

Drill bores of the appropriate diameter depending on the type of connection to be made on the structural element; remove any dust from inside the bores and install the Glass Connect L fibreglass connectors, as indicated in the technical data sheet, anchoring them to the support using Resinglass chemical anchoring agent.

Alternatively, appropriately bent Steel Dryfast stainless steel helical bars can be used. The quantity and arrangement of the connectors will be defined by the designer; 4 connectors per m² are recommended.

Lay the Glass Net A305 corner element at the edges; it must be placed at the centre-line of the total thickness of the mortar, ensuring an overlap of at least 10 cm between the corner element and the meshes of the Glass Net range. In overlapping areas, it is recommended to use the appropriate connectors.

Then wet the substrate until fully saturated and apply the chosen mortar, ensuring complete coverage of the system. The application can also be carried out in several layers depending on the final thickness required, between 3 and 5 cm. Allow the surfaces to cure for at least 24 hrs.

Certificates and marks



Abstract

CRM Glass Net system
Supply and installation of a CRM (Composite Reinforced Mortar) system for compressive strengthening of masonry piers applied on both sides of load-bearing walls, CE-marked, with European Technical Assessment (ETA), made with bi-directional FRP mesh consisting of AR fibreglass cords completely impregnated with thermosetting resin (total mass 315 g/m²) installed with hygroscopic and breathable inorganic mortar based on pure natural hydraulic lime NHL 3.5 - such as Glass Net CRM made with Glass Net 315 in combination with Geocalce G Antisismico by Kerakoll. Characteristics of the mesh: mesh size 50x52 mm, nominal cross-sectional area 8.33 mm² (weft) and 5 mm² (warp), typical tensile strength 486.11 MPa (weft) and 567.98 MPa (warp), typical ultimate strain 2.05% (weft) and 1.88% (warp), typical tensile elastic modulus 24.67 GPa (weft) and 28.78 GPa (warp), typical knot shear strength 0.62 (weft) and 0.84 kN (warp). Certified characteristics of the mortar: G/M15 mortar class (EN 998/2), R1 PCC resistance class (EN 1504-3), permeability to water vapour 15 to 35 (EN 1745), compressive strength after 28 days ≥ 15 N/mm² (EN 1015-11), elastic modulus 9.23 GPa (EN 13412), adhesion to the substrate after 28 days > 1.0 N/mm² – FB: B (EN 1015-12). Transversal connections are made with 4 elements per m², using “L” shaped fiberglass rebars installed on both sides with an internal overlap of at least 10 cm, for an average thickness of the load-bearing wall of 50 cm, grouted with a chemical anchoring agent - such as Glass Connect L8 in combination with Resinglass by Kerakoll. Characteristics of the rebar: nominal section area 50.24 mm², typical tensile strength 727.3 MPa, elastic modulus 44 GPa, break warp 2.38%, anchoring length 100 mm. Characteristics of the resin: CE-marked, suitable for seismic applications compliant with C1 and C2 performance levels, axial tensile strength 24,3 N/mm². The procedure will be conducted as follows: eventual preparation of the surfaces to be strengthened by demolishing and removing the existing plaster/render; repair of any cracks by binding and/or consolidating with injection of fluid mortar (to be accounted for separately) and final dusting by low-pressure water washing; creation and cleaning of the through-bore of a suitable diameter according to the diameter of the rebars, taking into account the overlapping of the rebars inside the bore; insertion of the connectors inside the bore and fastening by means of a chemical anchoring agent; positioning of the mesh, taking care to distance it from the substrate by means of fastening to the connectors; preparation and laying of the mortar with a plastering machine in a total thickness of 3-5 cm on each side. The quantification is calculated per unit area of reinforced masonry including any overlaps.

| Technical Data compliant with Kerakoll Quality Standard | |
|---------------------------------------------------------|---------------------------------------------------|
| Corner mesh technical information | |
| Material | AR glass pre-impregnated with thermosetting resin |
| Weight of impregnated mesh | ≈ 305 g/m ² |
| Nominal section of cords: | |
| - weft | 5.27 mm ² |
| - warp | 3.21 mm ² |
| Bars/metre per side: | |
| - weft | 26 n/m |
| - warp | 26 n/m |
| Mesh size: | |
| - weft | 38 mm |
| - warp | 38 mm |
| Height of the corner element | = 100 cm |
| Length of the short side | 25 cm |
| Shelf life | unlimited |
| Pack | 35 pcs. box |

| Performance | | | |
|----------------------------------------------|--|-------------------------------|----------------------------------------|
| Glass Net A305 for CRM systems - ETA 25/0350 | | | |
| Mechanical characteristics | | Test Method | Performance |
| Bar tensile strength (average value) | | Annex D EAD 340392-00-0104 | $F_{u,mc} = 1.85 \text{ kN}$ |
| Bar tensile strength (characteristic value) | | Annex D EAD 340392-00-0104 | $F_{u,mc} = 1.42 \text{ kN}$ |
| | | | weft warp |
| Modulus of elasticity (average value) | | | 28.6 GPa 48 GPa |
| Elastic modulus (characteristic value) | | | 24.3 GPa 40.3 GPa |
| Knot shear strength (average value) | | | 0.08 kN 0.13 kN |
| Knot shear strength (characteristic value) | | | 0.06 kN 0.1 kN |
| Glass transition temperature | | EN ISO 11357-2 | $T_g = 59.96 \text{ }^{\circ}\text{C}$ |
| Installation conditions | | | |
| Maximum temperature (air and substrate) | | | +60 °C |
| Minimum temperature (air and substrate) | | | -10 °C |
| Relative air humidity | | | irrelevant |
| Service conditions | | | |
| Maximum temperature (air and substrate) | | | +60 °C |
| Minimum temperature (air and substrate) | | | -10 °C |
| Relative air humidity | | | irrelevant |

Warning

- abide by any standards and national regulations

→ when handling the material wear protective clothing and goggles, and follow the instructions regarding methods for applying the material

→ store the material under cover in a dry place, well away from substances that might damage it
- the product is an item according to the definitions of the EC Regulation No. 1907/2006 and therefore does not require a Safety Data Sheet

→ for any other issues, contact Kerakoll Technical Customer Service: + 39 0536.811.516 www.kerakoll.com/contatti



The Rating classifications refer to the GreenBuilding Rating Manual 2012. This information was last updated in April 2025; please note that additions and/or amendments may be made over time by KERAKOLL SpA; for the latest version, see www.kerakoll.com. KERAKOLL SpA shall therefore be liable for the validity, accuracy and updating of information provided only when taken directly from its institutional website. The technical data sheet given here is based on our technical and practical knowledge. As it is not possible for us to directly check the conditions of your building site and the execution of the work, this information represents general indications that do not bind Kerakoll in any way. Therefore, it is advisable to perform a preliminary test to verify the suitability of the product for your purposes.